

BEST AVAILABLE COPY

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



0423 SEP


INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ :	A1	(11) International Publication Number:	WO 98/55891
G02B 6/42, 6/24, 6/26		(43) International Publication Date:	10 December 1998 (10.12.98)
(21) International Application Number:	PCT/US98/09363	(81) Designated States:	AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, GM, GW, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).
(22) International Filing Date:	1 June 1998 (01.06.98)	(30) Priority Data:	
60/048,573 08/965,798	4 June 1997 (04.06.97) 7 November 1997 (07.11.97)	US	US
(71) Applicant (for all designated States except US): LASERTRON, INC. [US/US]; 11 Oak Park, Bedford, MA 01730 (US).		(72) Inventors; and	
(73) Inventors/Applicants (for US only): KORN, Jeffrey [US/US]; 67 Ashbury Street, Lexington, MA 02173 (US). CONOVER, Steven, D. [US/US]; 7 Hillside Lane, Chelmsford, MA 01824 (US). SHARFIN, Wayne, F. [US/US]; 9 Loring Road, Lexington, MA 02173 (US). YANG, Thomas, C. [US/US]; 104 Crooked Spring Road, North Chelmsford, MA 01863 (US).		(74) Agents:	REYNOLDS, Leo, R. et al.; Hamilton, Brook, Smith & Reynolds, P.C., Two Militia Drive, Lexington, MA 02173 (US).

(54) Title: FLAT TOP, DOUBLE-ANGLED, WEDGE-SHAPED FIBER ENDFACE

(57) Abstract

An improved fiber endface shape for increasing coupling of optical power from a source into fiber and its manufacture are disclosed. The inventive tip comprises a cleaved end surface that is preferably substantially orthogonal to the fiber's axis and a first and second polished, angled surfaces intersecting the end surface. Break-lines between the angled surfaces and the end surface fall near an edge of a cladding-core interface and preferably outside that interface when the fiber and transmitted light are such that a substantial portion of the light is transmitted in the cladding. A spatial intensity profile of light exiting from the tip is detected during manufacture and is used to monitor the polishing of the angled surfaces. Tests have shown that the inventive tip achieves the coupling efficiency associated with the double-angled wedge-shaped fiber tips while maintaining much of the ease of manufacture associated with the single-angle wedge tips.



FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		

-1-

FLAT TOP, DOUBLE-ANGLED, WEDGE-SHAPED FIBER ENDFACE

RELATED APPLICATION

This application claims priority to U.S. Patent Application No. 08/965,798 filed on November 7, 1997, which is incorporated herein in its entirety, and which claims the 5 benefit of U.S. Provisional Application No. 60/048,573, filed June 4, 1997, the entire teachings of which are also incorporated herein by this reference.

BACKGROUND OF THE INVENTION

In optical fiber communication systems, and optical fiber light transmission systems generally, it is typically important to increase the efficiency with which light 10 from a source is coupled into the fiber. One of the most common applications is in communications systems to couple light from a single-transverse-mode light source, e.g., semiconductor laser, into a single-mode optical fiber. Historically, there has been a trade-off between high coupling efficiency and ease of manufacture. The following examples illustrate this principle:

15 1. Bulk optics

This is a popular technique in which lens are used to focus the light from the semiconductor laser onto the endface facet of the fiber. It can provide high-coupling efficiency if adequate lenses are used. The fact that multiple components, typically 1 or 20 2 lenses, are needed greatly increases the complexity of implementation and the reliability risk, however.

2. Hyperbolic fiber endfaces

The technique has provided coupling of 99% of the power from a single-mode laser into a single-mode fiber by using a high-power infrared laser to machine a hyperbolic surface on the fiber endface or tip. A hyperbola is the ideal shape for fiber coupling.

3. Single-angle wedge-shaped fiber endfaces

This has been used to couple 980 nanometer pump lasers to single-mode fibers. While it has the positive feature of being easy to manufacture, the achievable coupling efficiency has been limited to between 65 and 70%.

5 4. Double-angled wedge-shaped fiber tips

This technique is a compromise between hyperbolic fiber endfaces and the single-angle wedge-shaped fiber endfaces described above. It provides higher coupling efficiency than single-angle wedge-shaped endfaces, but not as high as hyperbolic endfaces. It is significantly easier to manufacture and implement than hyperbolic endfaces, but not as 10 easy as single-angle wedge-shaped fiber endfaces. To completely specify and manufacture the double-angled wedged-shaped fiber tip, four independent angles, having one of only two different values, and the location of three lines of intersection must be fabricated with sufficient precision.

SUMMARY OF THE INVENTION

15 The present invention is directed to an improved fiber endface shape and its manufacturing process. It achieves the coupling efficiency associated with the double-angled wedge-shaped fiber tips while maintaining the ease of manufacture associated with the single-angle wedge tips.

In general, according to one aspect, the invention relates to optical fibers, which 20 include a core and surrounding cladding for transmitting electromagnetic radiation, and specifically the tips or endfaces that usually receive input radiation from a light source. The inventive tip comprises an end surface that is preferably substantially orthogonal to the axis, a first angled surface intersecting the end surface, and a second angled surface also intersecting the end surface.

In the preferred embodiment, break-lines between the angled surfaces and the end surface fall near an edge of a cladding-core interface and preferably outside that interface when the fiber and transmitted light are such that a substantial portion of the light is transmitted in the cladding.

- 5 In other embodiments, break-lines are substantially parallel to each other, with the first and second surfaces being opposed to each other on opposite sides of the fiber.

In still other embodiments, additional angled surfaces are added. In each case, the angled surfaces intersect the end surface at break-lines, preferably falling near the cladding-core interface.

- 10 In general, according to another aspect, the invention also relates to a method for manufacturing a tip for an optical fiber. This process comprises first cleaving an end surface in the fiber. At least first and second surfaces are then formed, angled relative to the end surface.

- 15 In the preferred embodiment, a spatial intensity profile of light exiting from the tip is detected, which is used to monitor the polishing of the first and/or second angled surfaces.

The above and other features of the invention including various novel details of construction and combinations of parts, and other advantages, will now be more particularly described with reference to the accompanying drawings and pointed out in 20 the claims. It will be understood that the particular method and device embodying the invention are shown by way of illustration and not as a limitation of the invention. The principles and features of this invention may be employed in various and numerous embodiments without departing from the scope of the invention.

BRIEF DESCRIPTION OF THE DRAWINGS

In the accompanying drawings, reference characters refer to the same parts throughout the different views. The drawings are not necessarily to scale; emphasis has instead been placed upon illustrating the principles of the invention. Of the drawings:

- 5 Fig. 1 is a cross-sectional side view of the inventive fiber tip;
- Fig. 2 is an end view of the inventive fiber tip;
- Fig. 3 is a side view illustrating the coupling between the laser and the fiber when the optical axis of the laser is not parallel to the optical axis of the fiber; and
- Figs. 4A-4C illustrate the steps for manufacturing the inventive fiber tip.

10 DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENT

Fig. 1 is a cross-sectional view showing a fiber tip or endface constructed according to the principles of the present invention.

The single-mode optical fiber 100 has three surfaces fabricated on tip 110. Planar surfaces S1 and S2 slant obliquely backward from the terminal end, on opposed 15 sides of the fiber. The slopes of surfaces S1 and S2 are identified as θ_1 and θ_2 , respectively, measured from a plane extending perpendicularly to the mechanical and optical axis 112 of the fiber 100. Preferably, θ_1 and θ_2 are approximately 25° . A workable range for θ_1 and θ_2 is between 10 and 40° . In one implementation, one of θ_1 or θ_2 is more 25° and the other is less 25° . The third surface S3 is perpendicular to the 20 mechanical and optical axis 112 of the fiber 100.

As best shown in Fig. 2, the angled surfaces S1 and S2 join the end surface S3 at break-lines BL1 and BL2, respectively. These break-lines pass near the edge of the fiber's core 102, or cladding-core interface, 105.

In the illustrated embodiment, the angled surfaces S1-S2 oppose each other on 25 opposite sides of the fiber 100, and thus the break-lines BL1 and BL2 are parallel to

each other. It should be noted that the break-lines BL1 and BL2 need not be parallel to each other for all applications. It may be desirable in some cases to configure the angled surfaces S1 and S2 to not be directly opposed to each other.

- Moreover, it is not necessary that the break-lines BL1-BL2 intersect or pass over
- 5 the core 102 of the fiber 100. In the illustrated example, the break-lines BL1 and BL2 pass to the outside of cladding-core interface 105. This configuration is typically used when the fiber mode's wavelength is sufficiently longer than the cut-off wavelength; a significant portion of the mode will thus occupy the cladding region 104.

- As illustrated by Fig. 3, angles θ_1 and θ_2 of surfaces S1 and S2 need not be equal
- 10 to each other. This might be necessary when the optical axis 210 of the light source 200 is not parallel to the optic axis of the fiber as illustrated. This is equivalent to having a tilted facet or laser beam.

- The present invention is not limited to elliptical core fibers or circularly symmetric fibers. It can be used with elliptical clad, panda, elliptical core, bow-tie, tapered, and
- 15 circularly symmetric fibers. Moreover, more than two angled surfaces may be formed at the tip 110 to achieve a more hyperbolic end, while still maintaining the perpendicular end surface S3. Still further, the fiber tip may have a dielectric coating.

Figs. 4A-4C illustrate the technique for manufacturing the inventive fiber tip.

- As shown in Fig. 4A, the end 110 of the fiber 100 is flat cleaved. This step is
- 20 preferably performed using well-known fiber cleaving processes.

As shown in Fig. 4B, the surface S1 is then polished into the fiber. The extent of the polishing and thus the extent of surface S1 is controlled in response to a pattern of light 310 exiting the fiber, which is produced by injecting light into the opposite end.

An intensity profile 312 is monitored using photodetector 300. In the preferred embodiment, the photodetector is located remotely from and parallel to surface S3. The intensity is scanned in a direction perpendicular to break-line BL1 in the plane of the photodetector 300 to plot the spatial intensity profile 312.

5 The shape and location of the peak 314 in the spatial intensity profile is used to control the polishing of the surface. Generally, the location of the peak's maxima 315 in a direction parallel to surface S3 is indicative of the location of the break-line BL1, and the peak's shape or extent 318 is indicative of the angle θ_1 . Thus, the profile is descriptive of the two variables in the machining of surface S1.

10 Generally, the polishing of surface S1 is controlled so that the location of the breakline BL1 either falls only over the cladding 104 or in some cases may also enter a portion of the core 102. This choice depends generally on the frequency of light transmitted by the fiber relative to the fiber's dimensions and thus to what extent the light is transmitted within the fiber's cladding 104.

15 As shown in Fig. 4C, in the next step, surface S2 is polished into the fiber tip. Again, the spatial intensity profile 312 on the detector 300 is used to monitor polishing to achieve the desired location of break-line BL2 and angle θ_2 by reference to the maxima and breadth of peak 316.

20 Experience from manufacturing suggests that it is helpful to allow the fiber 100 to bend somewhat during the polishing process. It is theorized that this adds some curvature to surfaces S1 and S2 and rounds over the break-lines BL1 and BL2 achieving a more hyperbolic cross-section.

In other embodiments, additional, *i.e.*, more than two, angled surfaces, such as a total of four, are polished into the fiber tip. While increasing polishing steps, the tip better approximates a circularly hyperbolic shape.

There are a number of advantages of the present invention relative to the double-angled wedge-shaped fiber tip. First, the number of independent variables in the manufacture of the fiber is reduced to four, the location of the break-lines and the angles of surfaces S1 and S2. There are seven independent variables in the manufacture of the double-angled wedge-shaped angle tip. Additionally, the cleaved surface S3 is not subjected to polishing and therefore retains the superior optical properties of a smooth cleaved surface relative to a polished surface.

While this invention has been particularly shown and described with references to preferred embodiments thereof, it will be understood by those skilled in the art that various changes in form and detail may be made therein without departing from the spirit and scope of the invention as defined by the appended claims.

CLAIMS

What is claimed is:

1. An optical fiber including a core and surrounding cladding for transmitting electromagnetic radiation along an axis of the fiber, the fiber being adapted to receive the radiation at a tip from a light source, the tip comprising:
 - 5 an end surface that is substantially orthogonal to the axis;
 - a first angled surface defining a first break-line at an intersection between the first angled surface and the end surface, the first break-line falling near an edge of the core; and
 - 10 at least a second angled surface defining at least a second break-line at an intersection between the second angled surface and the end surface, the second break-line falling near the edge of the core.
2. The fiber described in Claim 1, wherein the first and second break-lines pass over the core.
- 15 3. The fiber described in Claim 1, wherein the first and second break-lines pass only over the cladding but near the core.
4. The fiber described in Claim 1, wherein the first and second break-lines are substantially parallel to each other.
5. The fiber described in Claim 1, wherein the first and second break-lines are not parallel to each other.
- 20 6. The fiber described in Claim 1, wherein the first and second angled surfaces are opposed to each other on opposite sides of the fiber.

-9-

7. The fiber described in Claim 1, wherein the first and second angled surfaces are formed at different angles relative to an axis of the fiber.
8. The fiber described in Claim 1, wherein the first and second angled surfaces are formed at approximately the same angle relative to an axis of the fiber.
- 5 9. A method for manufacturing a tip for an optical fiber including a core and surrounding cladding for transmitting electromagnetic radiation along an axis of the fiber, the process comprising:
 - cleaving an end surface in the fiber;
 - polishing a first angled surface, which defines a first break-line at an intersection between the first angled surface and the end surface, until the break-line falls near an edge of the core; and
 - polishing a second angled surface, which defines a second break-line at an intersection between the second angled surface and the end surface, until the second break-line falls near the edge of the core.
- 10 15 10. The method described in Claim 9, further comprising:
 - detecting a spatial intensity profile of light exiting from the tip; and
 - using the spatial intensity profile to monitor the polishing of the first and/or second angled surfaces.
11. The method described in Claim 9, wherein the fiber is cleaved so that the end surface is substantially orthogonal to an axis of the fiber.
- 20 12. The method described in Claim 9, further comprising polishing the first and second angled surfaces at different angles relative to an axis of the fiber.

-10-

13. The method described in Claim 9, further comprising polishing the first and second angled surfaces at the same angle relative to an axis of the fiber.
14. An optical fiber including a core and surrounding cladding for transmitting electromagnetic radiation along an axis of the fiber, the fiber having a tip comprising:
 - 5 a cleaved surface;
 - a first polished surface angled relative to and intersecting the cleaved surface; and
 - 10 at least a second polished surface angled relative to and intersecting the cleaved surface.
15. The fiber described in Claim 14, wherein an intersection between the first angled surface and the end surface falls near an edge of the core of the fiber.
16. The fiber described in Claim 15, wherein an intersection between the second angled surface and the end surface falls near an edge of the core of the fiber.

- 11 -

AMENDED CLAIMS

[received by the International Bureau on 21 October 1998 (21.10.98)
original claims 14-16 amended; new claim 17 added;
remaining claims unchanged (3 pages)]

1. An optical fiber including a core and surrounding cladding for transmitting electromagnetic radiation along an axis of the fiber, the fiber being adapted to receive the radiation at a tip from a light source, the tip comprising:
 - 5 an end surface that is substantially orthogonal to the axis;
 - a first angled surface defining a first break-line at an intersection between the first angled surface and the end surface, the first break-line falling near an edge of the core; and
 - 10 at least a second angled surface defining at least a second break-line at an intersection between the second angled surface and the end surface, the second break-line falling near the edge of the core.
2. The fiber described in Claim 1, wherein the first and second break-lines pass over the core.
- 15 3. The fiber described in Claim 1, wherein the first and second break-lines pass only over the cladding but near the core.
4. The fiber described in Claim 1, wherein the first and second break-lines are substantially parallel to each other.
- 20 5. The fiber described in Claim 1, wherein the first and second break-lines are not parallel to each other.
6. The fiber described in Claim 1, wherein the first and second angled surfaces are opposed to each other on opposite sides of the fiber.

-12-

7. The fiber described in Claim 1, wherein the first and second angled surfaces are formed at different angles relative to an axis of the fiber.
8. The fiber described in Claim 1, wherein the first and second angled surfaces are formed at approximately the same angle relative to an axis of the fiber.
- 5 9. A method for manufacturing a tip for an optical fiber including a core and surrounding cladding for transmitting electromagnetic radiation along an axis of the fiber, the process comprising:
 - cleaving an end surface in the fiber;
 - polishing a first angled surface, which defines a first break-line at an intersection between the first angled surface and the end surface, until the break-line falls near an edge of the core; and
 - polishing a second angled surface, which defines a second break-line at an intersection between the second angled surface and the end surface, until the second break-line falls near the edge of the core.
- 15 10. The method described in Claim 9, further comprising:
 - detecting a spatial intensity profile of light exiting from the tip; and
 - using the spatial intensity profile to monitor the polishing of the first and/or second angled surfaces.
11. The method described in Claim 9, wherein the fiber is cleaved so that the end 20 surface is substantially orthogonal to an axis of the fiber.
12. The method described in Claim 9, further comprising polishing the first and second angled surfaces at different angles relative to an axis of the fiber.
13. The method described in Claim 9, further comprising polishing the first and second angled surfaces at the same angle relative to an axis of the fiber.

-13-

14. An optical fiber/laser coupling system, the optical fiber including a core and surrounding cladding for transmitting electromagnetic radiation along an axis of the fiber, the system comprising:
 - a laser light source; and
 - the fiber having a tip comprising: a cleaved surface; a first polished surface angled relative to and intersecting the cleaved surface; and
 - at least a second polished surface angled relative to and intersecting the cleaved surface.
15. The system described in Claim 14, wherein an intersection between the first angled surface and the end surface falls near an edge of the core of the fiber.
16. The system described in Claim 15, wherein an intersection between the second angled surface and the end surface falls near an edge of the core of the fiber.
17. The fiber described in Claim 1, wherein the end surface is maintained as a cleaved surface to maintain favorable optical properties when transmitting light from a laser light source.

1/2




FIG. 1




FIG. 2




FIG. 3




FIG. 4A




FIG. 4B




FIG. 4C

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 98/09363

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 G02B6/42 G02B6/24 G02B6/26

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 G02B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 086 155 A (RIVOALLAN LOIC) 17 August 1983 see abstract; claim 9; figure 6 see page 2, line 14 - line 36 see page 3, line 10 - line 20 ---	1-4,6, 8-11, 13-16
X,P	WO 97 42533 A (LASER POWER CORP ;FLINT GRAHAM W (US)) 13 November 1997 see abstract; figures 5,11 see page 9, line 18 - page 10, column 24 ---	1,3,4,6, 8,9,11, 13-16
A	PATENT ABSTRACTS OF JAPAN vol. 003, no. 040 (E-102), 6 April 1979 & JP 54 019762 A (FUJITSU LTD), 14 February 1979 see abstract -----	1,2,9,14

Further documents are listed in the continuation of box C.

Patent family members are listed in annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

Date of mailing of the international search report

18 September 1998

24/09/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl.
Fax: (+31-70) 340-3016

Authorized officer

Jakober, F

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 98/09363

Patent document cited in search report		Publication date		Patent family member(s)		Publication date
EP 0086155	A	17-08-1983	FR	2521053 A		12-08-1983
WO 9742533	A	13-11-1997	US	5734766 A		31-03-1998
			AU	2748897 A		26-11-1997
			US	5771324 A		23-06-1998

THIS PAGE BLANK (USPTO)

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- BLACK BORDERS**
- IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- FADED TEXT OR DRAWING**
- BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- SKEWED/SLANTED IMAGES**
- COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- GRAY SCALE DOCUMENTS**
- LINES OR MARKS ON ORIGINAL DOCUMENT**
- REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.

THIS PAGE BLANK (USPTO)